



Austral Coffee Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	176
Mean Soaked Compressive Strength (MPa)	162
Flexural Strength (MPa) / Average Soaked	10.9
Flexural Strength (MPa) / Average Dry	9.9
Mean Luminous Reflectance / Average Soaked	14.43
Mean Luminous Reflectance / Average Dry	30.21
Abrasion Resistance	3



OUTDOOR FINISH
EXFOLIATED

[Disclaimer at the bottom — the copywriting might change from product to product, but it will be more or less a sentence for each.]