



AUSTRALIAN GRANITE

Calca Red Data Sheet


Wet Slip Resistance

Finish	Value	Classification
Exfoliated	59	P5

Analysis

Results

Water Absorption (% by Weight)	0.18%
Coefficient of Thermal Expansion (mm/mm/°C x 10 ⁻⁶)	8.4
Soaked Flexural Strength (MPa) / Average	11.4
Bulk Density (Kg/m ³)	2603
Abrasion Resistance (Ha)	151



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]